

The carbon footprint of this grade is : 352 g eq CO₂ /m²

This grade is made with 65% recycled fibres and is guaranteed 100% recyclable (norm EN 13430).

Papers complying with the regulation Bfr XXXVI.

<u>Item designation</u>					Cylinder thickness		Number of flutes/m
DF G 825					G	0,5	554
Caliper (+/- 10% / ISO3034) :							
Weight (+/- 7% / ISO536) :							

0,86 mm or 33,7 mil
387 g/m² or 79,3 lb/1000 ft²

Papers composition

Inner liner	Fluting 1	Centre liner 1	Fluting 2	Centre liner 2	Fluting 2	Outer liner
TL135	CAN100					K125

Technical characteristics

Theoretical values

Tests	Burst(kPa)	Bulk (Cm3/g)
	ISO 2759	ISO 3037
Average	853	2,21
Min	810	1,99

Averages figures for 95% of the measured values. All tests are carried out under conditions of 23°C and 50% RH. ISO 187

All papers used are subject to strict quality controls.

Edited : 01/09/2022