

The carbon footprint of this grade is : 393 in g eq CO₂/m² (Scopes 1+2+3)

This grade is made with 56% recycled fibres and is guaranteed 100% recyclable (norm EN 13430).

Papers complying with the regulation Bfr XXXVI.

Item designation DF G 841					Cylinder thickness		Number of flutes/m
Caliper (+/- 10% / ISO3034) :					G	0,5	554
Weight (+/- 7% /ISO536) :							

Papers composition

Inner liner	Fluting 1	Centre liner 1	Fluting 2	Centre liner 2	Fluting 2	Outer liner
KBC180	CAN100					COB125

Technical characteristics

Theoretical values

Tests	Burst(kPa)	Bulk (Cm3/g)
	ISO 2759	ISO 3037
Average	588	2,08
Min	558	1,87

Averages figures for 95% of the measured values. All tests are carried out under conditions of 23°C and 50% RH. ISO 187

All papers used are subject to strict quality controls.

Edited : 15/06/2022